

GP® TITANFLEX



GP® TITANFLEX - Gas and hydrocarbon barrier is a multi-layer, polyethylene membrane. GP® TITANFLEX is specifically designed, manufactured, tested and certified to perform as a methane, carbon dioxide, radon, ground gas, VOC, air & moisture and hydrocarbon protection system.

GP® TITANFLEX complies with the latest codes of practice as published by BRE, CIRIA (C748) and BSI (BS 8485:2015). Suitable for use as Ground Gas/Hydrocarbon protection for NHBC, **GREEN**, **AMBER1**, **AMBER 2** and **RED** site characterisations.

CHARACTERISTICS	TEST METHOD	UNIT	GP® TITANFLEX
PHYSICAL PROPERTIES			
THICKNESS	EN 1849-2	mm	0.5
WIDTH	EN 1849-2	m	2
LENGTH	EN 1849-2	m	50
WEIGHT	EN 1849-2	G/M ²	500
HYDRAULIC PROPERTIES			
WATER VAPOUR TRANSMISSION RATE	EN 1931	G/M ² /DAY	0.11-0.18
WATERTIGHTNESS (60 kPa)	EN 1928	-	PASS
WATERTIGHTNESS (196 kPa - 20m WATER HEAD) (BASEMENT APPLICATION)	EN 1928	-	PASS
MECHANICAL PROPERTIES			
RESISTANCE TO STATIC LOAD	EN 12730-B	Kg	≥20
PUNCTURE RESISTANCE	EN 12236	kN	≥2.0
TENSILE STRENGTH (MD)	EN 12311-1	N/50mm	>550
TENSILE STRENGTH (CMD)	EN 12311-1	N/50mm	>400
TENSILE ELONGATION (MD/CMD)	EN 12310-1	%	>550
TEAR RESISTANCE (MD/CMD)	EN 12310-1	N	>300
RESISTANCE TO IMPACT	EN 12691-B	mm	650
REACTION TO FIRE	EN 13501-1	CLASS	E
RESISTANCE TO ARTIFICIAL AGEING	EN 1296 / EN 1928	-	PASS
RESISTANCE TO CHEMICALS	EN 1847 / EN 1928	-	PASS
COMPLIANCE AND CERTIFICATION			
CE MARK - EN13967:2012			
NHBC STANDARDS COMPLIANT			
CIRIA C748 COMPLIANT			
BS 8485:2015 COMPLIANT			



- ⊕ Quick and easy installation.
- ⊕ Can be a fully welded system.
- ⊕ High resistance to ground gases.
- ⊕ Exceptional Chemical Resistance.
- ⊕ Manufactured to meet the most up to date British Standards and guidance.
- ⊕ Long Term Durability (performance guaranteed for the lifetime of the building).

Contact us to find out more information.
info@juta.co.uk | 01772 754177 | JUTA.CO.UK
 Melton Grove Works, Church Road, Lytham, FY8 5PL

JUTA



riba
product selector

TECHNICAL DATA

CHARACTERISTICS	TEST METHOD	UNIT	GP® TITANFLEX
VAPOUR PERMEABILITY 100% CONCENTRATION			
TRANSMISSION RATE OF BENZENE	EN ISO 15105-2	mg/m ² /day	<3.6
TRANSMISSION RATE OF TOLUENE	EN ISO 15105-2	mg/m ² /day	<13.8
TRANSMISSION RATE OF ETHYL BENZENE	EN ISO 15105-2	mg/m ² /day	<2.7
TRANSMISSION RATE OF XYLENES (M,P,O)	EN ISO 15105-2	mg/m ² /day	<7.7
TRANSMISSION RATE OF HEXANE	EN ISO 15105-2	mg/m ² /day	<0.6
TRANSMISSION RATE OF VINYL CHLORIDE	EN ISO 15105-2	mg/m ² /day	<0.05
TRANSMISSION RATE OF TRICHLOROETHENE (TCE)	EN ISO 15105-2	mg/m ² /day	<54.7
TRANSMISSION RATE OF TETRACHLOROETHENE (PCE)	EN ISO 15105-2	mg/m ² /day	<26.2
TRANSMISSION RATE OF NAPHTHALENE	EN ISO 15105-2	mg/m ² /day	<0.0006
TRANSMISSION RATE OF CIS-1,2-DICHLOROETHYLENE	EN ISO 15105-2	mg/m ² /day	<1.1
GAS PERMEABILITY			
METHANE PERMEABILITY	EN ISO 15105-1	ml/m ² /day/atm	0.13
METHANE PERMEABILITY (JOINTED)	EN ISO 15105-1	ml/m ² /day/atm	1.00
CARBON DIOXIDE PERMEABILITY	EN ISO 15105-1	ml/m ² /day/atm	3.01
VINYL CHLORIDE GAS PERMEABILITY	EN ISO 15105-1	ml/m ² /day/atm	0.04
RADON PERMEABILITY	K124/02/195	m ² /S	1.0 X 10 ⁻¹²
DURABILITY AND CHEMICAL RESISTANCE			
Chemical Resistance - SULFURIC ACID (10% Solution of Sulfuric Acid (H ₂ SO ₄)) 50° For 56 Days.	EN 14414-A	TENSILE STRENGTH RETAINED	100%
		RESULT	PASS
Chemical Resistance - BASIC (Calcium Hydroxide Saturated Suspension) 50° For 56 Days.	EN 14414-B	TENSILE STRENGTH RETAINED	100%
		RESULT	PASS
Chemical Resistance - SOLVENTS (35% Diesel, 35% Paraffin, 30% Oil Hd30 (Vol)) 50° For 56 Days.	EN 14414-C	TENSILE STRENGTH RETAINED	>80%
		RESULT	PASS
Chemical Resistance - SYNTHETIC LEACHATE (Mixture of 14 Acids, Chlorides, Sulphates & Phosphates) 50° for 56 days.	EN 14414-D	TENSILE STRENGTH RETAINED	100%
		RESULT	PASS
Resistance to Leaching - HOT WATER (Deionised water) 50° for 56 days.	EN 14415-A	TENSILE STRENGTH RETAINED	100%
		RESULT	PASS
Resistance to Leaching - AQUEOUS ALKALINE (Saturated Calcium Hydroxide) 50° for 56 days.	EN 14415-B	TENSILE STRENGTH RETAINED	100%
		RESULT	PASS
Resistance to Leaching - ORGANIC ALCOHOL (30% METHANOL, 30% ISOPROPANOL, 40% GLYCOL) 50° for 56 days.	EN 14415-C	TENSILE STRENGTH RETAINED	100%
		RESULT	PASS
Chemical Resistance - BENZENE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED	95% (MD) 102%(CMD)
		RESULT	PASS
Chemical Resistance - TOLUENE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED	94% (MD) 91%(CMD)
		RESULT	PASS
Chemical Resistance - ETHYL BENZENE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED	99% (MD) 97%(CMD)
		RESULT	PASS
Chemical Resistance - XYLENES - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED	91% (MD) 106%(CMD)
		RESULT	PASS
Chemical Resistance - TCE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED	99% (MD) 93%(CMD)
		RESULT	PASS
Chemical Resistance - PCE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED	93% (MD) 93%(CMD)
		RESULT	PASS
Chemical Resistance -NAPHTHALENE- 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED	101% (MD) 93%(CMD)
		RESULT	PASS
Chemical Resistance - HEXANE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED	99% (MD) 104%(CMD)
		RESULT	PASS

FOR THE NEEDS OF TODAY AND THE DEMANDS OF TOMORROW.