

PRODUCT DATA SHEET

Sika MonoTop®-610

CEMENTITIOUS STEEL REINFORCEMENT PRIMER & BONDING BRIDGE

PRODUCT DESCRIPTION

Sika MonoTop® -610 is a one component cementitious, polymer modified primer for reinforcement protection and also a bonding bridge for MonoTop concrete repair mortars.

USES

Sika MonoTop® -610 may be used to bond MonoTop concrete repair mortars to existing cementitious or steel substrates and provide additional corrosion protection to reinforcement in MonoTop concrete repair mortars especially in areas of low concrete cover and in the presence of chlorides.

CHARACTERISTICS / ADVANTAGES

- Only requires mixing with water
- Active corrosion inhibitors for added protection
- Sprayable by wet spray method
- Adjustable consistency
- Suitable for drinking water contact

APPROVALS / STANDARDS

Approved for potable water contact as part of a system
Reinforcement corrosion protection according to EN 1504-7(2006)
DoP 02 03 02 02 001 0 000001

PRODUCT INFORMATION

Chemical Base	Portland cement, polymer redispersable powder/liquid, selected aggregates and additives.
Packaging	25 kg bags
Appearance / Colour	Light Grey (Powder)
Shelf Life	12 months from date of production
Storage Conditions	Store properly in original unopened, sealed and undamaged packaging in dry and cool conditions.
Density	Fresh mortar density: ~ 2.0 kg/l

TECHNICAL INFORMATION

Tensile Adhesion Strength	Concrete	Steel
	~ 1.0 – 2.5 N/mm ²	~ 1.0 – 2.0 N/mm ²

SYSTEM INFORMATION

System Structure	Sika MonoTop® -610 is part of the Sika® MonoTop Concrete Repair System <ul style="list-style-type: none">▪ Sika® MonoTop-610: Bonding primer and reinforcement coating▪ Sika® MonoTop-612: Hand and wet spray applied repair mortar▪ Sika® MonoTop-614F: Pourable repair mortar▪ Sika® MonoTop-615: Hand and wet spray applied high build repair mortar▪ Sika® MonoTop-412N: Hand and wet spray applied high build repair mortar▪ Sika® MonoTop-630 Rapid: Hand applied repair mortar▪ Sika® MonoTop-620: Smoothing coat▪ Sika® FerroGard®-903+: Corrosion inhibitor
-------------------------	---

APPLICATION INFORMATION

Mixing Ratio	Water: Powder: 1:4.13 by volume <ul style="list-style-type: none">▪ For brush application: 1:4.75 by weight (5.25 litres of water per 25 kg bag)▪ For spray application: 1:5 parts by weight, 1:4.35 by volume (5 litres of water per 25 kg bag)
Consumption	This depends on the substrate roughness and thickness of layer applied. As a guide, <ul style="list-style-type: none">▪ Reinforcement Coating: ~ 2.0 kg/m² per coat▪ Bonding Primer: ~ 1.5 – 2.0 kg/m²
Layer Thickness	0.5 mm min. / 1.0 mm max.
Ambient Air Temperature	+5°C min. / +30°C max.
Substrate Temperature	+5°C min. / +30°C max.
Pot Life	~ 90 - 120 minutes (at +20°C)

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete:

Delaminated, weak, damaged and deteriorated concrete and where necessary sound concrete shall be removed by suitable mechanical or very high pressure waterblasting [up to 110 MPa (16500 psi)] techniques. Tying wire fragments, nails and other metal debris embedded in the concrete should be removed where possible.

The edges where concrete is removed should be cut at a minimum angle of 90° to avoid undercutting and a maximum angle of 135° to reduce the possibility of debonding with the top surface of the adjacent sound concrete and should be roughened sufficiently to provide a mechanical key between the original material and Sika MonoTop repair mortars.

Ensure sufficient concrete is removed from around reinforcement to allow coating and compaction of the repair material.

Steel reinforcement:

Surfaces should be prepared using abrasive blast cleaning techniques or high pressure waterblasting [up to 60 MPa (9000 psi)] techniques.

Where exposed reinforcement is contaminated with chloride or other material which may cause corrosion, the reinforcement shall be cleaned by low pressure waterblasting [up to 18 MPa (2700 psi)].

Bonding primer:

Pre-wet the concrete substrate. The surface should not be allowed to dry before application of the concrete repair mortar. The surface should achieve a dark matt appearance without glistening and surface pores and pits should not contain water.

Reference should also be made to BS EN1504-10:2003 for specific requirements.

MIXING

Sika MonoTop® -610 can be mixed with a slow speed (< 500 rpm) electric drill mixer. Pour the water in the correct proportion into a suitable mixing container. While stirring slowly, add the powder to the water. Mix thoroughly for at least 3 minutes to the required consistency.

APPLICATION

Reinforcement Corrosion Protection/Primer:

Apply first layer approx. 1 mm thick, using medium hard brush or spray gun to the cleaned reinforcement. Apply 2nd layer when the first coat is fingernail hard (~2 - 3 hours at +20°C). If the second coat of Sika MonoTop® -610 is allowed to dry prior to repair mortar application, then a fresh coat must be applied.

Bonding Primer/Bridge:

Apply using medium hard brush or spray gun to prepared substrate. To achieve good bond, Sika MonoTop® -610 must be applied well into the substrate, filling all pores.

Reference shall be made to BS EN1504-10:2003 for specific requirements.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened/cured material can only be mechanically removed.

FURTHER DOCUMENTS

LIMITATIONS

- Avoid application in direct sun and/or strong wind and/or rain.
- Do not add water over recommended dosage.
- Apply only to sound, prepared substrates.
- Protect freshly applied material from freezing.
- The bonding primer application also forms the second coat for the reinforcement coating.
- Care should be taken to ensure continuous application behind the reinforcement bars.
- When used as a bonding primer, the "grab" properties of the Sika MonoTop® -610 will reduce if it dries out before the repair mortar application. Repeat application if necessary.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet

Sika MonoTop®-610
February 2020, Version 01.02
020302020010000001

SikaMonoTop-610-en-GB-(02-2020)-1-2.pdf