

GP® DPC - Gas Resistant DPC is a unique single layer, embossed **High Performance DPC**. GP® DPC is specifically designed and manufactured to perform as a Methane, Carbon dioxide, Radon & Moisture resistant damp proof course.

GP® DPC complies with the latest codes of practice as published by BRE, CIRIA and BSI (BS EN 14909 and BS8485:2015). Suitable for use as a High Performance DPC for vertical and horizontal applications. Superior adhesion to mortar Is essential for buildings of 3+ storey height.



GP® I	DPC -HIGH PERFORMANCE DP	C	
Characteristic	Test Method	Unit	GP® DPC
	Physical Properties		
Thickness	EN 1849-2	mm	0.8
Width	EN 1849-2	mm	100-1200
Length	EN 1849-2	M	20
Mass	EN 1849-2	g/m²	730
	Hydraulic Properties		
Water Vapour Permeation	EN 1932	g/m²/day	0.09
Resistance to water penetration	EN 1928	Y	PASS
	Mechanical Properties		
Resistance to Static Load	EN 12730 - B	Kg	20
Tensile Strength (MD)	EN 12311 -1	N/mm²	24
Tensile Strength (CMD)	EN 12311 -1	N/mm²	22
Tensile Elongation (MD)	EN 12311 -1	%	398
Tensile Elongation (CMD)	EN 12311 -1	%	446
Resistance to Impact	EN 12691	mm	660
Resistance to tearing (nail shank) MD	EN 12310 - 1	N	700
Resistance to tearing (nail shank) CMD	EN 12310 - 1	N	750
oint Strength	EN 12317-2	N	520
Dural	bility and Chemical Resistan	ce	
Heat Ageing	EN 1926	-	Pass
Chemical Resistance	EN 1847	-/	Pass
Resistance to Fire	EN 13501-1	Class	F
Resistance to Low Temperature	EN 495-5		Pass @ -40°C
	Gas Permeability		
Radon Permeability	K124/02/95	m²/s	9.5 X 10 ⁻¹²
Methane Permeability	B5 EN ISO 15105 - 1	ml/m²/day/atm	33.9
Co	ompliance and Certification		
E Mark - EN13967:2012	YYY	YYY	
NHBC Standards Compliant			
35 EN 14909:2012 Compliant			
B5 8485:2015 Complaint			

Characteristic Shear Strength		
Pre-Compression (N/mm²)	Characteristic Shear Strength (N/mm²)	
0.2	0.14	
0.6	0.34	
1.0	0.52	

Contact us to find out more information.

info@juta.co.uk | 01772 754177 | JUTA.CO.UK

Melton Grove Works, Church Road, Lytham, FY8 5PL











Additional Information

JUTA GP® DPC has an embossed surface to create superior mortar adhesion which is essential when being used in 3+ storey applications. JUTA GP® DPC is complaint to B5 EN 14909:2012 and can be used in both vertical and horizontal applications.

HANDLING

Roll weights can be in excess of 5kg and hence appropriate care and equipment is required for unloading and handling.

STORAGE

Rolls of JUTA GP® DPC should be stored on stable/level ground and stacked not more than five rolls high, with no other material stacked on top. The rolls can be stored outdoors when packaged but should be protected from exposure to UV. JUTA GP® DPC is classified as non-hazardous and is chemically inert such that it will not react with any acid or alkali environment in which it is used.

INSTALLATION

JUTA GP® DPC must be installed in accordance with the guidelines laid out in B58215:1991, B58000: part 3 and B5 5628. It can be used in most common floor constructions and is installed in a similar manor to damp proof membrane. For external walls the DPC should be applied 150mm above the adjoining surface and should be linked to a DPM or Gas Resistant DPM in solid floors. The DPC should be applied to a fresh bed of mortar, completely free of projections that may puncture the material or impede the DPC from lying flat.

JOINTING AND SEALING

Sheets of JUTA GP® DPC must be clean, dry, and free from dirt and grease before application of jointing tape. JUTA GP® DPC may also be heat welded to the underlying Gas resistant membrane.

ACCESSORY PRODUCTS

JUTA GP® DPC is an accessory product for use in combination with GP® 1, GP® 2, GP®H GP®5AM, and GP® TITANTECH gas protective membranes. It is also compatible with a range of DPM and other DPC materials.

ADDITIONAL INFORMATION

For additional information or assistance, please contact JUTA UK directly.













