


- 1. Description** 6mm HDPE cusped drainage board with a PP geotextile filter/separator bonded to a single side.
- 2. Applications** Geofabrics FC6 geocomposite has been designed to provide a passive venting system for gasses and liquids.
- 3. Features**
- Optimised for maximum strength and performance
  - UV stabilised
  - Very high crush resistance
  - Excellent flow rate



	Test Standard	Unit	Mean Values		
<b>4. Mechanical Properties – Geocomposite</b> Compressive strength	EN ISO 25619-2	kPa	800		
<b>5. Mechanical Properties – Geotextile Filter</b> Tensile strength (MD/CMD)	EN ISO 10319	kN/m	9		
Static puncture (CBR)	EN ISO 12236	kN	1.4		
<b>6. Hydraulic Properties – Geotextile Filter</b> Water permeability $v_{H50}$	EN ISO 11058	l/(m <sup>2</sup> ·s)	100		
Apparent opening size	EN ISO 12956	µm	80		
<b>7. Hydraulic Properties – Geocomposite</b> In plane flow capacity (rigid/rigid)	EN ISO 12958	l/(m·s)	i = 1	i = 0.5	i = 0.1
@ 20kPa			2.0	1.5	0.65
@ 100kPa			2.0	1.5	0.60
@ 200kPa			2.0	1.5	0.55
<b>8. Physical Properties – Geocomposite</b> Thickness @ 20kPa	EN ISO 9863-1	mm	7		
Standard colour – Cuspate			Black		
Polymer – Cuspate			HDPE		
Polymer – Geotextile			PP		

Notes:

- a) Mean values indicate the arithmetic mean derived from the samples taken for any one test as defined in the standard – usually an overall mean of five samples. Mean values are subject to tolerances based on 95% confidence limits as published on the product CE declaration of performance.

- 9. Testing** All materials are tested every 6000m<sup>2</sup> in an UKAS accredited ISO 17025 laboratory to all mechanical properties prior to release.
- 10. Storage** The geocomposites are supplied in packaging designed to protect the product from damage during handling, storage, and degradation as a result of UV exposure. The product should be kept in appropriate packaging until such time that it is required for installation. The product is clearly and indelibly marked with the product name along the edge of the roll at regular intervals no greater than 5m. The packaging is labelled clearly to identify the product supplied in accordance with EN ISO 10320: Geotextile and Geotextile related products – Identification on site. Use slings where provided. Product weights are given on roll tickets. Use equipment appropriate to weight and dimension. Store and handle in accordance with good occupational hygiene and safety practice.

	Unit	Values
<b>11. Dimensions</b>		
Standard roll length	m	100
Standard roll width	m	0.97
Approximate roll weight	Kg	115

Geofabrics Limited, Skelton Grange Road, Stourton, Leeds LS10 1RZ, United Kingdom